

^{10}B in Form of Boric Acid for the Nuclear Industry



- Enriched Boric Acid for use as a chemical shim for excess neutron absorption in the primary circuit of PWRs using high burnup or MOX fuel cores.
- In these PWRs neutron absorption of natural Boric Acid is insufficient. Solubility of Boric Acid limits the boron concentration in primary circuit water to be used as neutron poison.
- Today more and more enriched Boric Acid (95 % enriched in ^{10}B) is used by NPPs.

Specification

- Material ¹⁰B-Boron-10 in form of crystalline Boric Acid
- Enrichment ¹⁰B > 95 at%
- Purity > 99.95 wt%

Impurities in µg/g

As	<	0.5
Ca	<	1
Cl	<	1
Co	<	0.1
Cr	<	0.1
F	<	1
Fe	<	0.5
Heavy metals (e.g.Pb)	<	0.5
Hg	<	0.5
H ₂ O insolubles	<	10
Na	<	0.5
PO ₄	<	0.5
SO ₄	<	1
Ti	<	0.1

NUKEM GmbH

Industriestrasse 13, 63755 Alzenau, Germany, **T** +49 (0)6023 911611, **F** +49 (0)6023 911614
E info@nukem.de, **I** www.nukemgroup.com

NUKEM, Inc.

39 Old Ridgebury Road, Section B-1, Box #9, Danbury, CT 06810-5100, USA
T +1 203 7789420, **F** +1 203 7789430, **E** info@nukeminc.com